

Schalldaten fiwo-Dämmstoffe

Frequenz	iso.30	aku.30	aku.60	aku.80
125	0.05	0.06	0.10	0.18
160	0.06	0.07	0.12	0.25
200	0.08	0.09	0.16	0.33
250	0.10	0.11	0.20	0.38
315	0.11	0.14	0.27	0.55
400	0.12	0.16	0.35	0.69
500	0.12	0.17	0.43	0.79
630	0.13	0.23	0.52	0.89
800	0.12	0.29	0.66	0.97
1000	0.29	0.46	0.82	1.00
1250	0.37	0.58	0.92	0.98
1600	0.45	0.69	0.96	0.95
2000	0.57	0.80	0.96	0.94
2500	0.65	0.88	0.92	0.98
3150	0.73	0.90	0.89	0.99
4000	0.76	0.88	0.94	0.98

fiwo
Industrie Schwarzland
Sommeriestrasse 37
8580 Amriswil
Telefon 071 424 66 66

Schallabsorptionsgrad nach EN ISO 10534-2:2001

