

REPORT NUMBER: 103129336MID-001a
ORIGINAL ISSUE DATE: July 16, 2017
REVISED DATE: NA

EVALUATION CENTER
Intertek
8431 Murphy Drive
Middleton, WI 53562

RENDERED TO:

Serge Ferrari
Zone Industrielle BP 54
38352 La Tour Du Pin Cedex
38110 LA TOUR DU PIN
France
Catherine Merillon
catherine.merillon@sergeferrari.com

PRODUCT EVALUATED: Soltis B92
EVALUATION PROPERTY: NFPA 701-2015, METHOD 2
STANDARD METHODS OF FIRE TESTS FOR FLAME
PROPAGATION OF TEXTILES AND FILMS with a Flat Sheet (Section 13.1.3)

Report of Testing Soltis B92 for compliance with the applicable requirements of the following criteria: NFPA 701-2015, METHOD 2 Standard Methods of Fire Tests for Flame Propagation Of Textiles and Films for Flat Sheets (Section 13.1.3)

"This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program."

1 Table of Contents

1	TABLE OF CONTENTS	2
2	INTRODUCTION.....	3
3	TEST SAMPLES	3
3.1.	SAMPLE SELECTION.....	3
3.2.	SAMPLE AND ASSEMBLY DESCRIPTION	3
4	TESTING AND EVALUATION METHODS	3
4.1.	TEST STANDARD 1.....	3
4.2.	DEVIATION FROM STANDARD METHOD	3
5	TESTING AND EVALUATION RESULTS	4
5.1.	RESULTS AND OBSERVATIONS.....	4
6	CONCLUSION	5
7	REVISION SUMMARY	5

2 Introduction

Intertek has conducted testing for Serge Ferrari on Soltis B92 to assess the propagation of flame beyond the area exposed to the ignition source. Testing was conducted in accordance with NFPA 701-2015, Method 2 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films for Flat Sheets (See section 13.1.3). This evaluation began July 13, 2017 and ended July 13, 2017.

3 Test Samples

3.1. SAMPLE SELECTION

Samples were submitted to Intertek directly from the client. Samples were not independently selected for testing. Samples were received at the Evaluation Center on July 3, 2017 in good condition.

3.2. SAMPLE AND ASSEMBLY DESCRIPTION

Sample Name: Soltis B92

Sample Description: Polyester yarns coated with PVC flame retardant on both sides; on the back face an opacifiant PVC film.

Weight: 650 g/m² +/-5% Thickness: 0.60mm +/-10% Polyester: 28% PVC flame retardant + PVC film opacifiant: 72%

The test specimens were cut into 5.25 in. by 47.75 in. samples by Intertek. All samples were conditioned in an oven at 105°C ± 3°C for no less than 1 hour but no more than 3 hours before testing.

Test room conditions: 77.3°F and 60% R.H.

4 Testing and Evaluation Methods

4.1. TEST STANDARD 1

Ten specimens of material 5.25 inches by 47.25 inches were cut with their long dimension parallel to the length direction ("with" machine). Specimens were removed from the oven one at a time and tested immediately. The specimens were supported with clips in a three-sided vertical column and exposed to an 11" flame for two minutes. The flame impinged approximately 7 inches on the specimen.

No specimen should continue flaming for more than two seconds. Length of char should not exceed 17.1 inches from the bottom edge of the specimen for Flat Sheets (See section 13.1.3). No flaming on floor of apparatus should last longer than two seconds.

4.2. Deviation from Standard Method

No deviations from the standard.

5 Testing and Evaluation Results

5.1. RESULTS AND OBSERVATIONS

Equipment: Oven #1200, Stopwatch #1221, Scale #1396, Test Cabinet #1203

Specimen	After Flame Duration (sec)	Floor Flaming (sec)	Char Length (in)
1	0	0	10.13
2	0	0	6.13
3	0	0	6.54
4	0	0	6.77
5	0	0	6.41
6	0	0	5.92
7	0	0	5.93
8	0	0	7.82
9	0	0	7.67
10	0	0	5.52
Average	0	0	6.88

	Specimen 1	Specimen 2	Specimen 3
Weight (g)	6.55	6.48	6.51
Length (mm)	100	100	100
Width (mm)	100	100	100
g/m ²	655	648	651
		Average	651.33

Observations:

This sample passed the criteria for NFPA 701-2015 method 2 for flat sheets (see section 13.1.3)

6 Conclusion

Intertek has conducted testing for Serge Ferrari on Soltis B92 to assess the propagation of flame beyond the area exposed to the ignition source. Testing was conducted in accordance with NFPA 701-2015, Method 2 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films for flat sheets (See section 13.1.3).

The sample PASSED the testing criteria for NFPA 701-2015, Method 2 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films for flat sheets (See section 13.1.3).

The conclusions of this test report may not be used as part of the requirements for Intertek product certification. Authority to Mark must be issued for a product to become certified.

INTERTEK

Reported by:

Sandy Osborne
Lab Technician I, Verification Center

Reviewed by:

Bryan Bowman
Chemist, Verification Center

7 Revision Summary

DATE	SUMMARY
July 16, 2017	Original Report
